



# Technical data sheet

**Application :**

**Heavy duty air filter paper**

**CX9958A-WX**

Property	Unit	Numerical Range
Grammage	G/m <sup>2</sup>	110-115
Thickness	mm	0.3±0.05
Air Permeability	L/m <sup>2</sup> .sec	130-150
Max. Pore Size	µm	≤45
Average Pore Size	µm	41
Burst Strength	kPa	≥300
Stiffness	mN.m	≥4.5
Corrugation Depth	mm	0.43-0.48

**Remarks:**

1. Test Conditions:temperature23±1°C,Humidity:50±2%.
2. The testing area for grammage test is 0.01 m<sup>2</sup>.
3. Air permeability Test:△p=200pa:Area of the test plate=20cm<sup>2</sup>.
4. Bubble method:The max.pore size is the figure corresponding to the pressure difference when the first bubble appears.
5. Stiffness test:Taber.

## Contact

**Web:** [www.tjs-nonwoven.com](http://www.tjs-nonwoven.com)

**Tel/Fax:** +86 10 64783159

**Mail:** [info@tjs-nonwoven.com](mailto:info@tjs-nonwoven.com)

**Phone:** +86 17501070309

**Add:** North of Shifu Street and west of Shengxing Road, Xinji City Hebei, China

**Tianjinsheng Non-Woven Technology Co., Ltd.**