



# Technical data sheet

Application:

**P8001T-P**

Oil bypass filter paper

Property	Unit	Numerical Range
Grammage	G/m <sup>2</sup>	285-295
Thickness	mm	0.8±0.05
Air Permeability	L/m <sup>2</sup> .sec	90-110
Max. Pore Size	μm	≤50
Average Pore Size	μm	45
Burst Strength	kPa	≥450
Stiffness	mN.m	≥10
Corrugation Depth	mm	0
Resin Content (Acrylic)	%	3-7
Volatility	%	3-5

**Remarks:**

1. Test Conditions:temperature23±1°C,Humidity:50±2%.
2. The testing area for grammage test is 0.01 m<sup>2</sup>.
3. Air permeability Test:Δp=200pa:Area of the test plate=20cm<sup>2</sup>.
4. Bubble method:The max.pore size is the figure corresponding to the pressure difference when the first bubble appears.
5. Stiffness test:Taber.

## Contact

Web: [www.tjs-nonwoven.com](http://www.tjs-nonwoven.com)

Tel/Fax: +86 10 64783159

Mail: [info@tjs-nonwoven.com](mailto:info@tjs-nonwoven.com)

Phone: +86 17501070309

Add: North of Shifu Street and west of Shengxing Road, Xinji City Hebei, China

**Tianjinsheng Non-Woven Technology Co., Ltd.**