

Technical data sheet

Application :

K803-W

Dust collector filter paper

Property	Unit	Numerical Range
Grammage	G/m ²	130-140
Thickness	mm	0.5±0.05
Air Permeability	L/m ² .sec	340-360
Max. Pore Size	μm	≤85
Average Pore Size	μm	80
Burst Strength	kPa	≥280
Stiffness	mN.m	≥4.0
Corrugation Depth	mm	0.2-0.3
Resin Content (Acrylic)	%	18-22
Volatility	%	3-5

Remarks:

1. Test Conditions:temperature23±1°C,Humidity:50±2%.
2. The testing area for grammage test is 0.01 m².
3. Air permeability Test:Δp=200pa:Area of the test plate=20cm².
4. Bubble method:The max.pore size is the figure corresponding to the pressure difference when the first bubble appears.
5. Stiffness test:Taber.

Contact

Web: www.tjs-nonwoven.com

Tel/Fax: +86 10 64783159

Mail: info@tjs-nonwoven.com

Phone: +86 17501070309

Add: North of Shifu Street and west of Shengxing Road, Xinji City Hebei, China

Tianjinsheng Non-Woven Technology Co., Ltd.