

Technical data sheet

Application:

CWF-811802

Long fiber

Property	Unit	Value	Method
Basis Weight	g/m ²	185±4	GB/T451.2-2002
Thickness	μm	380±10	GB/T451.3-2002
Dry tensile strength (CD)	KN/m	4.17±0.3	GB/T12914
Dry tensile strength (MD)	KN/m	5.68±0.3	GB/T12914
Wet tensile strength (CD)	KN/m	1.26±0.3	GB/T12914
Wet tensile strength (MD)	KN/m	1.83±0.3	GB/T12914
Wet expansion rate (CD)	%	< 0.3	GB/T22899
Opacity	%	88	GB/T1543
Water absorption	s	> 300	
Moisture	%	5.0±0.5	GB/T462

Contact

Web: www.tjs-nonwoven.com

Tel/Fax: +86 10 64783159

Mail: info@tjs-nonwoven.com

Phone: +86 17501070309

Add: North of Shifu Street and west of Shengxing Road, Xinji City Hebei, China

Tianjinsheng Non-Woven Technology Co., Ltd.